

## NOTES:

- SUBSTRATE: POLYCARBONATE
- 2. OPERATING TEMPERATURE (°C): -30 TO +100 (MAXIMUM OF 240 HOURS)
- 3. DAMAGE THRESHHOLD (PULSED): 0.22 @ 1064nm J/cm² @ 10ns
- 4. TRANSMISSION (%): 85

EDGES CUT AND SEAMED

6. RoHS: COMPLIANT





## PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2		
SHAPE	PLANO	PLANO		
WAVELENGTH RANGE	400 - 1600nm	400 - 1600nm		
DIFFUSING ANGLE (FWHM)	25 ±2.5°	25 ±2.5°		
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED		

		l
THIRD ANGLE PROJECTION		
ALL DIMS IN	mm	

B	<b>Edmund Optic</b>	S®
TITLE	25° DIFFUSING ANGLE Ø12.5mm UNMOUNTED HOLOGRAPHIC DIFFUS	
DWG NO	35866	SHEET

1 OF 1