## NOTES:

1. SUBSTRATE: FUSED SILICA


2. COATING (APPLY ACROSS COATING APERTURE):


S1: R(AVG) ≥ 98% @ 340-488nm @ 0° AOI R(AVG) ≥ 98% @ 320-450nm @ 45° AOI FOR ALL POLARIZATION R(AVG) ≥ 98% @ 320-450nm @ 45° FOR S-POLARIZATION

S2: NONE

3. FINE GRIND SURFACE







## SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

Shape	S1 PLANO	S2 PLANO			<sup>®</sup> Edmund Optics <sup>®</sup>
CLEAR APERTURE	> 90	N/A			Ø10mm, 320 - 450nm BROADBAND λ/10
SURFACE QUALITY	20-10	COMMERCIAL POLISH	THIRD ANGLE		MIRROR
SURFACE FLATNESS	λ/10	N/A			
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED	ALL DIMS IN mm	DWG NO	37559 SHEET 1 OF 1